




Thermoelectric Cooler XLT2416

RoHS 2002/95/EC Compliant


Performance Values

Hot Side Temperature (°C)	27°C	50°C
Δ Tmax (°C-dry N ₂):	56.0	63.5
Qmax (watts):	33.9	37.3
I _{max} (amps):	14.7	14.6
V _{max} (vdc):	3.6	4.0
AC Resistance (ohms):	0.20	---



Mechanical Characteristics

ACR Number Code	ACR Range (ohms)	
1	0.166	0.169
2	0.169	0.172
3	0.172	0.175
4	0.175	0.178
5	0.178	0.181
6	0.181	0.184
7	0.184	0.187
8	0.187	0.190
9	0.190	0.193
10	0.193	0.196
11	0.196	0.199
12	0.199	0.202
13	0.202	0.205
14	0.205	0.208
15	0.208	0.211



Ordering Options

Model Number	Description
XLT2416-03AC	Leadwires
XLT2416-04AC	Leadwires, Sealed
XLT2416-05AC	Leadwires, ACR Number Coded

Features


- **RoHS 2002/95/EC compliant**
- Specifically designed for thermal cycling applications
- Capable of rapid heating and cooling rates
- Proven High Reliability (Data available upon request)
- Rugged construction
- Porched configuration for enhanced leadwire strength
- Rated operating temperature of 130°C
- Height tolerance of ± 0.0005 in. (± .013 mm) allows for multiple module applications
- Modules with number coded AC resistance available




Performance Curves

Environment: One atmosphere dry nitrogen

Hot Side Temperature: 27°C
TA(C) = 27



Hot Side Temperature 50°C
TA(C) = 50



For performance information in a vacuum or with hot side temperatures other than 27°C or 50°C, consult one of our Applications Engineers.

Installation

XLT coolers are typically mounted under compression using thermal grease or flexible graphite products. Consult Marlow Industries' Thermoelectric Installation Guide for more details. For additional information, please contact one of our application engineers for technical support.

Addresses

Marlow Industries, Inc.
10451 Vista Park Road
Dallas Texas 75238-1645
214-340-4900 (tel)
214-341-5212 (fax)
www.marlow.com

Marlow Industries Europe
Aberdeen House, South Road
Haywards Heath
West Sussex RH164NG UK
+44 (0)1444-443404 (tel)
+44 (0)1444-443334(fax)

Marlow Industries Japan
1-1-8-401
Uehara, Shibuya-ku
Tokyo, Japan 151-0064
+81 (3) 5454-5280 (tel)
+81 (3) 5454-5281(fax)