

Rev. V5

Features

- ♦ 0603 Outline
- ♦ Surface Mount
- ♦ 25µm I-Region Length Devices
- ♦ No Wirebonds Required
- ♦ Silicon Nitride Passivation
- ♦ Polymer Scratch Protection
- ◆ Low Parasitic Capacitance and Inductance
- ♦ High Average and Peak Power Handling

Description

This device is a silicon, glass PIN diode surmount chip fabricated with M/A-COM's patented HMICTM process. This device features two silicon pedestals embedded in a low loss, low dispersion glass. The diode is formed on the top of one pedestal and connections to the backside of the device are facilitated by making the pedestal sidewalls electrically conductive. Selective backside metallization is applied producing a surface mount device. This vertical topology provides for exceptional heat transfer. The topside is fully encapsulated with silicon nitride and has an additional polymer layer for scratch and impact protection. These protective coatings prevent damage to the junction and the anode air-bridge during handling and assembly.


Applications

These packageless devices are suitable for usage in moderate incident power, $\leq 50 \text{dBm/C.W.}$ or where the peak power is $\leq 75 \text{dBm}$, pulse width is $1 \mu \text{S}$, and duty cycle is 0.01%. Their low parasitic inductance, 0.4 nH, and excellent RC constant, make these devices a superior choice for higher frequency switch elements when compared to their plastic package counterparts.

Absolute Maximum Ratings¹ @ TA = +25°C (unless otherwise specified)

Parameter	Absolute Maximum					
Forward Current	500 mA					
Reverse Voltage	- 135 V					
Operating Temperature	-55°C to +125°C					
Storage Temperature	-55 °C to +150°C					
Junction Temperature	+175°C					
C.W. Incident Power	+44dBm MADP-017025					
C.W. Ilicident Fower	+47dBM MADP-030025					
Peak Incident Power (dBm)	+50 dBm, 10µS, 1% duty					
Mounting Temperature	+280°C for 30 seconds					
	·					

Case Style ODS 1314



Chip Dimensions

DIM	INCI	HES	M	М
	Min	Max	Min	Max
Α	0.060	0.062	1.525	1.575
В	0.031	0.032	0.775	0.825
С	0.004	0.008	0.102	0.203
D	0.019	0.021	0.475	0.525
Е	0.019	0.021	0.475	0.525
F	0.019	0.021	0.475	0.525
G	0.029	0.031	0.725	0.775

Notes:

- 1) Backside metal: 0.1microns thick.
- 2) Yellow area with hatch lines indicate backside ohmic gold
- 3) Both devices have same outline dimensions (A to G).
- 1) Exceeding these limits may cause permanent damage

ADVANCED: Data Sheets contain information regarding a product M/A-COM Technology Solutions is considering for development. Performance is based on target specifications, simulated results, and/or prototype measurements. Commitment to develop is not guaranteed.

PRELIMINARY: Data Sheets contain information regarding a product M/A-COM Technology Solutions have under development. Performance is based on prolipering tasts. Specifications are

aniori prototype measurements. Commitment to develop is not guaranteeu. PRELIMINARY: Data Sheets contain information regarding a product M/A-COM Technology Solutions has under development. Performance is based on engineering tests. Specifications are typical. Mechanical outline has been fixed. Engineering samples and/or test data may be available. Commitment to produce in volume is not guaranteed.

- North America Tel: 800.366.2266 Europe Tel: +353.21.244.6400
- India Tel: +91.80.4155721
 China Tel: +86.21.2407.1588
 Visit www.macomtech.com for additional data sheets and product information.



Rev. V5

Electrical Specifications @ $T_A = 25$ °C (unless otherwise noted)

Parameter	Symbol	Conditions	Units	Min	Тур	Max	Min	Тур	Max
				MADP-017025		MADP-030025			
Capacitance 1	Ст	- 40V, 1MHz ¹	pF		0.23	0.29		0.50	0.56
Capacitance 1	Ст	- 40V, 1GHz ^{1,3}	pF		0.23			0.50	
Capacitance ¹ , 85°C	Ст	- 40V, 1GHz ^{1,3}	pF		0.22			-	
Resistance ²	Rs	+10mA, 1GHz ^{2,3}	Ω		1.01			0.65	
Resistance ²	Rs	+70mA, 1GHz ^{2,3}	Ω		0.64			0.45	
Resistance ² , 85°C	Rs	+10mA, 1GHz ^{2,3}	Ω		1.48			-	
Resistance ² , 85°C	Rs	+70mA, 1GHz ^{2,3}	Ω		1.03			-	
Forward Voltage	V _F	+10mA	V		0.74	0.90		0.73	0.90
Reverse Leakage Current	I _R	-135V	μA		-	10		-	10
Third Order Intercept Point	IP3	F1 = 1800MHz F2 = 1810MHz Input Power = +39dBm CW I bias = +70mA	dBm		76			77	
C.W. Thermal Resistance	R_{qJL}	I _H = 0.5A, I _L = 10mA	°C/W		30			13	
Lifetime	TL	+10mA / -6mA (50 % - 90 % V)	uS		2.3			2.8	

Notes:

- 1) Total capacitance, C_T, is equivalent to the sum of Junction Capacitance ,C_j, and Parasitic Capacitance, C_{par}.
- 2) Series resistance R_S is equivalent to the total diode resistance : $R_S = R_j$ (Junction Resistance) + R_C (Ohmic Resistance)
- R_S and C_T are measured on an HP4291A Impedance Analyzer with die mounted in an ODS213 package with 80/20, Au/Sn solder.

MADP-0XX025 Series Typical Spice Parameters @ +25°C


Spice Parameter	N	RS	IS	IK	в۷	IBV	Ct	CJO	۸٦	М	FC	Cpar_Cj
Units	1	Ω	Α	(mA)	(Volts)	(μ A)	(pF)	(pF)	(Volts)	-	-	(F)
MADP-017025-1314	1.1	1.4	5.1E-15	12.6	175	10	0.38	0.10	0.17	0.50	0.12	2.7E-13
MADP-030025-1314	1.1	1.3	7.8E-15	12.7	175	10	0.80	0.27	0.12	0.50	0.07	5.3E-13


India Tel: +91.80.4155721
 China Tel: +86.21.2407.1588
 Visit www.macomtech.com for additional data sheets and product information.




Rev. V5

MADP-0XXX15 Series Typical Performance Curves @ +25°C Ct vs. V Rs vs. I







Ct vs. Freq.




Ls vs. Freq.



Rs vs. Freq.



Ls vs. I



- ADVANCED: Data Sheets contain information regarding a product M/A-COM Technology Solutions is considering for development. Performance is based on target specifications, simulated results, and/or prototype measurements. Commitment to develop is not guaranteed. **PRELIMINARY:** Data Sheets contain information regarding a product M/A-COM Technology Solutions has under development. Performance is based on engineering tests. Specifications are typical. Mechanical outline has been fixed. Engineering samples and/or test data may be available. Commitment to produce in volume is not guaranteed.



Rev. V5

Assembly Guidelines

Handling

All semiconductor chips should be handled with care to avoid damage or contamination from perspiration and skin oils. The use of plastic tipped tweezers or vacuum pickups is strongly recommended for individual components. Bulk handling should insure that abrasion and mechanical shock are minimized.

Bonding

Attachment to a circuit board is made simple through the use of surface mount technology. Mounting pads are conveniently located on the bottom surface of these devices and are removed from the active junction locations. These devices are well suited for solder or conductive epoxy attachment onto hard and soft substrates. The use of 60/40, Pb/Sn, 80/20, Au/Sn or any other lead-free solder is recommended to achieve the lowest series resistance and optimum heat sink.

When soldering these devices to a hard substrate, hot gas die bonding is preferred. We recommend utilizing a vacuum tip and applying a force of 40 - 60 grams to the top surface of the device. When soldering, position the die so that its mounting pads are aligned with the circuit board mounting pads and reflow the solder by heating the circuit trace near the mounting pads while applying 40 to 60 grams of force perpendicular to the top surface of the die. Both mounting pads should be heated simultaneously so that the solder under both pads flows at the same time. The solder joint should not be made one at a time. By doing so, would create an un-equal heat flow and potentially create thermal stress to the chip.

Solder reflow should not be performed by causing heat to flow through the top surface of the die. Die should be uniformly heated in a re-flow oven. Proper flow is easily determined looking down from the top since the HMIC glass is transparent and the edges of the mounting pads can be visually inspected through the die after attachment is complete. A typical soldering process profile and handling instructions are provided in Application Notes, M538 Surface Mounting Instructions and M541 Bonding and Handling Procedures on the MA-COM website at www.macomtech.com.

Conductive silver epoxy may also be used for die attachment, in lower Incident power applications where the average power is < 1 W. Apply a thin controlled amount approximately 1- 2 mils thick to minimize ohmic and thermal stresses. Take care not to bridge the gap between the chip pads with epoxy. A thin epoxy fillet should be visible around the perimeter of the pads after placement to ensure full coverage. Cure per epoxy per manufacturer's recommended schedule.

Ordering Information

Part Number	Package
MADP-017025-13140G	100 piece gel pack
MADP-017025-13140P	3000 piece reel
MADP-030025-13140G	100 piece gel pack
MADP-030025-13140P	3000 piece reel

India Tel: +91.80.4155721
 China Tel: +86.21.2407.1588

Visit www.macomtech.com for additional data sheets and product information.