
Y5V Dielectric

General Specifications






Y5V formulations are for general-purpose use in a limited temperature range. They have a wide temperature characteristic of +22% -82% capacitance change over the operating temperature range of -30° C to $+85^{\circ}$ C.

Y5V's high dielectric constant allows the manufacture of the highest capacitance value in a given case size.

These characteristics make Y5V ideal for decoupling applications within limited temperature range.

PART NUMBER (see page 3 for complete part number explanation)



PERFORMANCE CHARACTERISTICS


Capacitance Range	2200 pF to 22 µF
Capacitance Tolerances	+80 -20%
Operating Temperature Range	–30°C to +85°C
Temperature Characteristic	+22% to -82% max. within operating temperature
Voltage Ratings	10, 16, 25 and 50 VDC (+85°C)
Dissipation Factor	For 50 volts: 5.0% max. For 16 and 25 volts: 7% max. For 10 volts: 10% max.
Insulation Resistance (+25°C, RVDC)	10,000 megohms min. or 1000 M Ω - μF min., whichever is less
Dielectric Strength	250% of rated voltage for 5 seconds at 50 mamp max. current
Test Voltage	1.0 Vrms ± 0.2 Vrms
Test Frequency	1 KHz



Y5V Dielectric

Typical Characteristic Curves**





SUMMARY OF CAPACITANCE RANGES VS. CHIP SIZE

Style	10V	16V	25V	50V
0402*	2.2nF - 0.1µF	2.2nF - 0.1µF	2.2nF - 22nF	2.2nF - 10nF
0603*	2.2nF - 1µF	2.2nF - 0.33µF	2.2nF - 0.22µF	2.2nF - 56nF
0805*	10nF - 4.7µF	10nF - 2.2µF	10nF - 1µF	10nF - 0.33µF
1206*	10nF - 10µF	10nF - 4.7µF	10nF - 2.2µF	10nF - 1µF
1210*	10nF - 22µF	0.1µF - 10µF	0.1µF - 4.7µF	0.1µF - 1µF
1812*	\rightarrow	\rightarrow	0.15µF - 1.5µF	1.5nF - 1.5µF
1825*	\rightarrow	\rightarrow	0.47µF - 1.5µF	0.47µF - 1.5µF
2220	_	_	_	1μF - 1.5μF
2225	\rightarrow	\rightarrow	0.68µF - 2.2µF	0.68µF - 1.5µF

* Standard Sizes ** For additional information on performance changes with operating conditions consult AVX's software SpiCap.



Y5V Dielectric

Capacitance Range

PREFERRED SIZES ARE SHADED

						œ	0			α	ם			E	_			Π			Π						
SIZE		040)2*			060)3*			08	05			12	206			12	10		18	12*	18	25*	2220*	22	25*
Standard Reel Packaging	A	ll Pa	aper			All P	aper		Pap	er/Er	nbos	ssed	Pap	ber/E	mbo	ssed	Pap	er/Er	mbos	sed	All Eml	bossed	All Em	bossed	All Embossed	All Emb	possed
(L) Length MM (in.)		.00 ± 40 ±	± .10 .004	.)		1.60 .063 ±				2.01 .079 :				3.20 .126 :					± .20 ± .008)	4.50 (.177 ±			±.30 ±.016)	5.7 ± 0.4 (.225 ± .016)	5.72 (.225 ±	
(W) Width MM (in.)		50 ±					£.15			1.25 .049 :	± .20)		1.60 .063 :	± .20	1		2.50	± .20		3.20 (.126 ±	± .20	6.40	±.40 ±.016)	5.0 ± 0.4 (.197 ± .016)	6.35 (.250 ±	± .25
(T) Max. Thickness MM (in.)	(.60	0	7	(0	.,		1.	30	-,		1.	50 59)	-,		1.7	70		1. (.0	70	1.	.70 167)	2.30 (.090)	1.	70
(t) Terminal MM (in.)		25 ±		8)	(£.15	5)			± .25				± .25		(.50 ±	± .25 ± .010)	.61 ±	± .36	.61 :	± .36 ± .014)	.64 ± .39 (.025 ± .015)		± .39
WVDC	<u> </u>		25	50	10	16	25	50	<u>`</u>	16	25	-		16		-	10		25	50	25	50	25	50	50	25	50
Cap 2200 (pF) 2700 3300																										-w-	
3900 4700 5600																									\square		<u> </u>
6800 8200																									₹		
Cap .01 (μF) .012																											
.015 .018		_	_																								
.022 .027																											
.033 .039 .047																											
.056 .068 .082																											
.10 .12																											
.15		_										\langle / \rangle	_								1/////						
.18 .22 .27																											
.33 .39 .47											///												/////		1		
.56 .68 .82																											////
1.0 1.2 1.5																				///							
1.8 2.2 2.7																					//////	/////	//////				(////
3.3 3.9 4.7																											
5.6 6.8 8.2																											
10.0 12.0 15.0																											
18.0																											

*Reflow soldering only.

NOTES: For low profile product, see page 19.








How to Order





EXAMPLE: 08055A101JAT2A



*C&D tolerances for $\leq 10 \text{ pF}$ values.

** Standard Tape and Reel material depends upon chip size and thickness. See individual part tables for tape material type for each capacitance value.

Note: Unmarked product is standard. Marked product is available on special request, please contact AVX. Standard packaging is shown in the individual tables.

Non-standard packaging is available on special request, please contact AVX.



Surface Mounting Guide

MLC Chip Capacitors



Component Pad Design

Component pads should be designed to achieve good solder filets and minimize component movement during reflow soldering. Pad designs are given below for the most common sizes of multilayer ceramic capacitors for both wave and reflow soldering. The basis of these designs is:

- Pad width equal to component width. It is permissible to decrease this to as low as 85% of component width but it is not advisable to go below this.
- Pad overlap 0.5mm beneath component.
- Pad extension 0.5mm beyond components for reflow and 1.0mm for wave soldering.

	Case Size	D1	D2	D3	D4	D5
D2	0402	1.70 (0.07)	0.60 (0.02)	0.50 (0.02)	0.60 (0.02)	0.50 (0.02)
	0603	2.30 (0.09)	0.80 (0.03)	0.70 (0.03)	0.80 (0.03)	0.75 (0.03)
1 D3	0805	3.00 (0.12)	1.00 (0.04)	1.00 (0.04)	1.00 (0.04)	1.25 (0.05)
	1206	4.00 (0.16)	1.00 (0.04)	2.00 (0.09)	1.00 (0.04)	1.60 (0.06)
≜	1210	4.00 (0.16)	1.00 (0.04)	2.00 (0.09)	1.00 (0.04)	2.50 (0.10)
D4	1808	5.60 (0.22)	1.00 (0.04)	3.60 (0.14)	1.00 (0.04)	2.00 (0.08)
▼	1812	5.60 (0.22)	1.00 (0.04))	3.60 (0.14)	1.00 (0.04)	3.00 (0.12)
→ D5 -	1825	5.60 (0.22)	1.00 (0.04)	3.60 (0.14)	1.00 (0.04)	6.35 (0.25)
	2220	6.60 (0.26)	1.00 (0.04)	4.60 (0.18)	1.00 (0.04)	5.00 (0.20)
ensions in millimeters (inches)	2225	6.60 (0.26)	1.00 (0.04)	4.60 (0.18)	1.00 (0.04)	6.35 (0.25)


REFLOW SOLDERING

Surface Mounting Guide

MLC Chip Capacitors




WAVE SOLDERING



Component Spacing

For wave soldering components, must be spaced sufficiently far apart to avoid bridging or shadowing (inability of solder to penetrate properly into small spaces). This is less important for reflow soldering but sufficient space must be allowed to enable rework should it be required.



Preheat & Soldering

The rate of preheat should not exceed 4°C/second to prevent thermal shock. A better maximum figure is about 2°C/second.

For capacitors size 1206 and below, with a maximum thickness of 1.25mm, it is generally permissible to allow a temperature differential from preheat to soldering of 150°C. In all other cases this differential should not exceed 100°C.

For further specific application or process advice, please consult AVX.

Cleaning

Care should be taken to ensure that the capacitors are thoroughly cleaned of flux residues especially the space beneath the capacitor. Such residues may otherwise become conductive and effectively offer a low resistance bypass to the capacitor.

Ultrasonic cleaning is permissible, the recommended conditions being 8 Watts/litre at 20-45 kHz, with a process cycle of 2 minutes vapor rinse, 2 minutes immersion in the ultrasonic solvent bath and finally 2 minutes vapor rinse.

Surface Mounting Guide



MLC Chip Capacitors

APPLICATION NOTES

Storage

Good solderability is maintained for at least twelve months, provided the components are stored in their "as received" packaging at less than 40°C and 70% RH.

Solderability

Terminations to be well soldered after immersion in a 60/40 tin/lead solder bath at 235 \pm 5°C for 2 \pm 1 seconds.


Leaching

Terminations will resist leaching for at least the immersion times and conditions shown below.


Termination Type	Solder	Solder	Immersion Time
	Tin/Lead/Silver	Temp. °C	Seconds
Nickel Barrier	60/40/0	260±5	30±1

Recommended Soldering Profiles





Wave



(Preheat chips before soldering) T/maximum 150°C

General

Surface mounting chip multilayer ceramic capacitors are designed for soldering to printed circuit boards or other substrates. The construction of the components is such that they will withstand the time/temperature profiles used in both wave and reflow soldering methods.

Handling

Chip multilayer ceramic capacitors should be handled with care to avoid damage or contamination from perspiration and skin oils. The use of tweezers or vacuum pick ups is strongly recommended for individual components. Bulk handling should ensure that abrasion and mechanical shock are minimized. Taped and reeled components provides the ideal medium for direct presentation to the placement machine. Any mechanical shock should be minimized during handling chip multilayer ceramic capacitors.

Preheat

It is important to avoid the possibility of thermal shock during soldering and carefully controlled preheat is therefore required. The rate of preheat should not exceed 4°C/second and a target figure 2°C/second is recommended. Although an 80°C to 120°C temperature differential is preferred, recent developments allow a temperature differential between the component surface and the soldering temperature of 150°C (Maximum) for capacitors of 1210 size and below with a maximum thickness of 1.25mm. The user is cautioned that the risk of thermal shock increases as chip size or temperature differential increases.

Soldering

Mildly activated rosin fluxes are preferred. The minimum amount of solder to give a good joint should be used. Excessive solder can lead to damage from the stresses caused by the difference in coefficients of expansion between solder, chip and substrate. AVX terminations are suitable for all wave and reflow soldering systems. If hand soldering cannot be avoided, the preferred technique is the utilization of hot air soldering tools.

Cooling

Natural cooling in air is preferred, as this minimizes stresses within the soldered joint. When forced air cooling is used, cooling rate should not exceed 4°C/second. Quenching is not recommended but if used, maximum temperature differentials should be observed according to the preheat conditions above.

Cleaning

Flux residues may be hygroscopic or acidic and must be removed. AVX MLC capacitors are acceptable for use with all of the solvents described in the specifications MIL-STD-202 and EIA-RS-198. Alcohol based solvents are acceptable and properly controlled water cleaning systems are also acceptable. Many other solvents have been proven successful, and most solvents that are acceptable to other components on circuit assemblies are equally acceptable for use with ceramic capacitors.

Packaging of Chip Components



Automatic Insertion Packaging


TAPE & REEL QUANTITIES

All tape and reel specifications are in compliance with RS481.

	8mm	12n	nm
Paper or Embossed Carrier	0805, 1005, 1206, 1210		
Embossed Only	0504, 0907	1505, 1805, 1808	1812, 1825 2220, 2225
Paper Only	0402, 0603		
Qty. per Reel/7" Reel	2,000 or 4,000 ⁽¹⁾	3,000	1,000
Qty. per Reel/13" Reel	10,000	10,000	4,000

⁽¹⁾ Dependent on chip thickness. Low profile chips shown on page 27 are 5,000 per reel for 7" reel. 0402 size chips are 10,000 per 7" reels and are not available on 13" reels. For 3640 size chip contact factory for quantity per reel.

REEL DIMENSIONS



Tape Size ⁽¹⁾	A Max.	B* Min.	С	D* Min.	N Min.	W ₁	W ₂ Max.	W ₃
8mm	330	1.5	13.0±0.20	20.2	50	$\begin{array}{c} 8.4\substack{+1.0\\-0.0}\\(.331\substack{+0.0\\-0.0}\end{array})\end{array}$	14.4 (.567)	7.9 Min. (.311) 10.9 Max. (.429)
12mm	(12.992)	(.059)	(.512±.008)	(.795)	(1.969)	$12.4^{\pm 2.9}_{-0.0} \\ (.488^{+.076}_{-0.0})$	18.4 (.724)	11.9 Min. (.469) 15.4 Max. (.607)

Metric dimensions will govern.

English measurements rounded and for reference only.


(1) For tape sizes 16mm and 24mm (used with chip size 3640) consult EIA RS-481 latest revision.



Embossed Carrier Configuration



8 & 12mm Tape Only



8 & 12mm Embossed Tape Metric Dimensions Will Govern

CONSTANT DIMENSIONS

Tape Size	D ₀	E	Po	P ₂	T Max.	T ₁	G ₁	G ₂
8mm and 12mm	$\begin{array}{c} 8.4 \substack{+0.10 \\ -0.0} \\ (.059 \substack{+.004 \\ -0.0}) \end{array}$	1.75 ± 0.10 (.069 ± .004)	4.0 ± 0.10 (.157 ± .004)	2.0 ± 0.05 (.079 ± .002)	0.600 (.024)	0.10 (.004) Max.	0.75 (.030) Min. See Note 3	0.75 (.030) Min. See Note 4

VARIABLE DIMENSIONS

Tape Size	B ₁ Max. See Note 6	D ₁ Min. See Note 5	F	P ₁	R Min. See Note 2	T ₂	W	A ₀ B ₀ K ₀
8mm	4.55 (.179)	1.0 (.039)	3.5 ± 0.05 (.138 ± .002)	4.0 ± 0.10 (.157 ± .004)	25 (.984)	2.5 Max (.098)	8.0 ^{+0.3} (.315 ^{+.012} 004)	See Note 1
12mm	8.2 (.323)	1.5 (.059)	5.5 ± 0.05 (.217 ± .002)	4.0 ± 0.10 (.157 ± .004)	30 (1.181)	6.5 Max. (.256)	12.0 ± .30 (.472 ± .012)	See Note 1
8mm 1/2 Pitch	4.55 (.179)	1.0 (.039)	3.5 ± 0.05 (.138 ± .002)	2.0 ± 0.10 0.79 ± .004	25 (.984)	2.5 Max. (.098)	8.0 ^{+0.3} -0.1 (.315 ^{+.012} 004)	See Note 1
12mm Double Pitch	8.2 (.323)	1.5 (.059)	5.5 ± 0.05 (.217 ± .002)	8.0 ± 0.10 (.315 ± .004)	30 (1.181)	6.5 Max. (.256)	12.0 ± .30 (.472 ± .012)	See Note 1

NOTES:

1. A₀, B₀, and K₀ are determined by the max. dimensions to the ends of the terminals extending from the component body and/or the body dimensions of the component. The clearance between the end of the terminals or body of the component to the sides and depth of the cavity (A₀, B₀, and K₀) must be within 0.05 mm (.002) min. and 0.50 mm (.020) max. The clearance allowed must also prevent rotation of the component within the cavity of not more than 20 degrees (see sketches C & D).


2. Tape with components shall pass around radius "R" without damage. The minimum trailer length (Note 2 Fig. 3) may require additional length to provide R min. for 12 mm embossed tape for reels with hub diameters approaching N min. (Table 4).

3. G, dimension is the flat area from the edge of the sprocket hole to either the outward deformation of the carrier tape between the embossed cavities or to the edge of the cavity whichever is less.


4. G₂ dimension is the flat area from the edge of the carrier tape opposite the sprocket holes to either the outward deformation of the carrier tape between the embossed cavity or to the edge of the cavity whichever is less.

5. The embossment hole location shall be measured from the sprocket hole controlling the location of the embossment. Dimensions of embossment location and hole location shall be applied independent of each other.

6. B_1 dimension is a reference dimension for tape feeder clearance only.



Side or Front Sectional View Sketch "C"




Top View Sketch "D



Paper Carrier Configuration



8 & 12mm Tape Only



8 & 12mm Paper Tape Metric Dimensions Will Govern

User Direction of Feed

CONSTANT DIMENSIONS

Tape Size	D ₀	E	Po	P ₂	T ₁	G ₁	G ₂	R MIN.
8mm and 12mm	1.5 ^{+0.1} (.059 ^{+.004} 000)	1.75 ± 0.10 (.069 ± .004)	4.0 ± 0.10 (.157 ± .004)	2.0 ± 0.05 (.079 ± .002)	0.10 (.004) Max.	0.75 (.030) Min.	0.75 (.030) Min.	25 (.984) See Note 2

VARIABLE DIMENSIONS


Tape Size	P ₁	F	w	A ₀ B ₀	Т
8mm	4.0 ± 0.10 (.157 ± .004)	3.5 ± 0.05 (.138 ± .002)	8.0 ^{+0.3} (.315 ^{+.012})	See Note 1	See Note 3
12mm	4.0 ± .010 (.157 ± .004)	5.5 ± 0.05 (.217 ± .002)	12.0 ± 0.3 (.472 ± .012)		
8mm 1/2 Pitch	2.0 ± 0.10 (.079 ± .004)	3.5 ± 0.05 (.138 ± .002)	8.0 ^{+0.3} (.315 ^{+.012})		
12mm Double Pitch	8.0 ± 0.10 (.315 ± .004)	5.5 ± 0.05 (.217 ± .002)	12.0 ± 0.3 (.472 ± .012)		


NOTES:

1. A₀, B₀, and T are determined by the max. dimensions to the ends of the terminals extending from the component body and/or the body dimensions of the component. The clearance between the ends of the terminals or body of the component to the sides and depth of the cavity (A₀, B₀, and T) must be within 0.05 mm (.002) min. and 0.50 mm (.020) max. The clearance allowed must also prevent rotation of the component within the cavity of not more than 20 degrees (see sketches A & B).

2. Tape with components shall pass around radius "R" without damage.

3. 1.1 mm (.043) Base Tape and 1.6 mm (.063) Max. for Non-Paper Base Compositions.





Bar Code Labeling Standard

AVX bar code labeling is available and follows latest version of EIA-556-A.




Bulk Case Packaging




BENEFITS

- Easier handling
- Smaller packaging volume (1/20 of T/R packaging)
- Easier inventory control
- Flexibility
- Recyclable

CASE DIMENSIONS







CASE QUANTITIES

Part Size	0402	0603	0805
Qty. (pcs / cassette)	80,000	15,000	10,000 (T=0.6mm) 5,000 (T≥0.6mm)