


# C0G (NP0) Dielectric

## General Specifications









C0G (NP0) is the most popular formulation of the “temperature-compensating,” EIA Class I ceramic materials. Modern C0G (NP0) formulations contain neodymium, samarium and other rare earth oxides.

C0G (NP0) ceramics offer one of the most stable capacitor dielectrics available. Capacitance change with temperature is  $0 \pm 30\text{ppm}/^\circ\text{C}$  which is less than  $\pm 0.3\% \Delta C$  from  $-55^\circ\text{C}$  to  $+125^\circ\text{C}$ . Capacitance drift or hysteresis for C0G (NP0) ceramics is negligible at less than  $\pm 0.05\%$  versus up to  $\pm 2\%$  for films. Typical capacitance change with life is less than  $\pm 0.1\%$  for C0G (NP0), one-fifth that shown by most other dielectrics. C0G (NP0) formulations show no aging characteristics.

The C0G (NP0) formulation usually has a “Q” in excess of 1000 and shows little capacitance or “Q” changes with frequency. Their dielectric absorption is typically less than 0.6% which is similar to mica and most films.

### PART NUMBER (see page 2 for complete part number explanation)

<b>0805</b>	<b>5</b>	<b>A</b>	<b>101</b>	<b>J</b>	<b>A</b>	<b>T</b>	<b>2</b>	<b>A</b>
Size (L" x W")	Voltage 6.3V = 6 10V = Z 16V = Y 25V = 3 50V = 5 100V = 1 200V = 2	Dielectric C0G (NP0) = A	Capacitance Code (in pF) 2 Sig. Digits + Number of Zeros	Capacitance Tolerance B = $\pm 0.10\text{ pF}$ C = $\pm 0.25\text{ pF}$ D = $\pm 0.50\text{ pF}$ F = $\pm 1\% (\geq 25\text{ pF})$ G = $\pm 2\% (\geq 13\text{ pF})$ J = $\pm 5\%$ K = $\pm 10\%$	Failure Rate A = Not Applicable	Terminations T = Plated Ni and Sn 7 = Gold Plated	Packaging 2 = 7" Reel 4 = 13" Reel 7 = Bulk Cass. 9 = Bulk	Special Code A = Std. Product
						Contact Factory For 1 = Pd/Ag Term	Contact Factory For Multiples	



# C0G (NP0) Dielectric

## Specifications and Test Methods



Parameter/Test	NP0 Specification Limits		Measuring Conditions		
<b>Operating Temperature Range</b>	-55°C to +125°C		Temperature Cycle Chamber		
<b>Capacitance</b>	Within specified tolerance		Freq.: 1.0 MHz ± 10% for cap ≤ 1000 pF 1.0 kHz ± 10% for cap > 1000 pF Voltage: 1.0Vrms ± .2V		
<b>Q</b>	<30 pF: Q≥ 400+20 x Cap Value ≥30 pF: Q≥ 1000				
<b>Insulation Resistance</b>	100,000MΩ or 1000MΩ - μF, whichever is less		Charge device with rated voltage for 60 ± 5 secs @ room temp/humidity		
<b>Dielectric Strength</b>	No breakdown or visual defects		Charge device with 300% of rated voltage for 1-5 seconds, w/charge and discharge current limited to 50 mA (max)		
<b>Resistance to Flexure Stresses</b>	Appearance	No defects	Deflection: 2mm Test Time: 30 seconds 1mm/sec		
	Capacitance Variation	±5% or ±.5 pF, whichever is greater			
	Q	Meets Initial Values (As Above)			
	Insulation Resistance	≥ Initial Value x 0.3			
<b>Solderability</b>	≥ 95% of each terminal should be covered with fresh solder		Dip device in eutectic solder at 230 ± 5°C for 5.0 ± 0.5 seconds		
<b>Resistance to Solder Heat</b>	Appearance	No defects, <25% leaching of either end terminal	Dip device in eutectic solder at 260°C for 60 seconds. Store at room temperature for 24 ± 2 hours before measuring electrical properties.		
	Capacitance Variation	≤ ±2.5% or ±.25 pF, whichever is greater			
	Q	Meets Initial Values (As Above)			
	Insulation Resistance	Meets Initial Values (As Above)			
	Dielectric Strength	Meets Initial Values (As Above)			
<b>Thermal Shock</b>	Appearance	No visual defects	Step 1: -55°C ± 2°	30 ± 3 minutes	
	Capacitance Variation	≤ ±2.5% or ±.25 pF, whichever is greater	Step 2: Room Temp	≤ 3 minutes	
	Q	Meets Initial Values (As Above)	Step 3: +125°C ± 2°	30 ± 3 minutes	
	Insulation Resistance	Meets Initial Values (As Above)	Step 4: Room Temp	≤ 3 minutes	
	Dielectric Strength	Meets Initial Values (As Above)	Repeat for 5 cycles and measure after 24 hours at room temperature		
<b>Load Life</b>	Appearance	No visual defects	Charge device with twice rated voltage in test chamber set at 125°C ± 2°C for 1000 hours (+48, -0). Remove from test chamber and stabilize at room temperature for 24 hours before measuring.		
	Capacitance Variation	≤ ±3.0% or ± .3 pF, whichever is greater			
	Q (C=Nominal Cap)	≥ 30 pF: Q≥ 350 ≥10 pF, <30 pF: Q≥ 275 +5C/2 <10 pF: Q≥ 200 +10C			
	Insulation Resistance	≥ Initial Value x 0.3 (See Above)			
	Dielectric Strength	Meets Initial Values (As Above)			
<b>Load Humidity</b>	Appearance	No visual defects	Store in a test chamber set at 85°C ± 2°C/ 85% ± 5% relative humidity for 1000 hours (+48, -0) with rated voltage applied. Remove from chamber and stabilize at room temperature for 24 ± 2 hours before measuring.		
	Capacitance Variation	≤ ±5.0% or ± .5 pF, whichever is greater			
	Q	≥ 30 pF: Q≥ 350 ≥10 pF, <30 pF: Q≥ 275 +5C/2 <10 pF: Q≥ 200 +10C			
	Insulation Resistance	≥ Initial Value x 0.3 (See Above)			
	Dielectric Strength	Meets Initial Values (As Above)			

# C0G (NP0) Dielectric

## Capacitance Range



PREFERRED SIZES ARE SHADED

SIZE	0201			0402			0603			0805					1206					
Soldering	Reflow Only			Reflow Only			Reflow/Wave			Reflow/Wave					Reflow/Wave					
Packaging	All Paper			All Paper			All Paper			Paper/Embossed					Paper/Embossed					
L) Length (in.)	MM 0.60 ± 0.03 (0.024 ± 0.001)	1.00 ± 0.10 (0.040 ± 0.004)	1.60 ± 0.15 (0.063 ± 0.006)	2.01 ± 0.20 (0.079 ± 0.008)	2.40 ± 0.20 (0.094 ± 0.008)	3.20 ± 0.20 (0.126 ± 0.008)														
(W) Width (in.)	MM 0.30 ± 0.03 (0.011 ± 0.001)	0.50 ± 0.10 (0.020 ± 0.004)	0.81 ± 0.15 (0.032 ± 0.006)	1.25 ± 0.20 (0.049 ± 0.008)	1.60 ± 0.20 (0.063 ± 0.008)	1.60 ± 0.20 (0.063 ± 0.008)														
(t) Terminal (in.)	MM 0.15 ± 0.05 (0.006 ± 0.002)	0.25 ± 0.15 (0.010 ± 0.006)	0.35 ± 0.15 (0.014 ± 0.006)	0.50 ± 0.25 (0.020 ± 0.010)	0.50 ± 0.25 (0.020 ± 0.010)	0.50 ± 0.25 (0.020 ± 0.010)														
WVDC	10	16	25	16	25	50	6.3	25	50	100	16	25	50	100	200	16	25	50	100	200
Cap (pF)	0.5	A	A	A	C	C	G	G	G	E	E	E	E	J	J	J	J	J	J	
	1.0	A	A	A	C	C	G	G	G	E	E	E	E	J	J	J	J	J	J	
	1.2	A	A	A	C	C	G	G	G	E	E	E	E	J	J	J	J	J	J	
	1.5	A	A	A	C	C	G	G	G	E	E	E	E	J	J	J	J	J	J	
	1.8	A	A	A	C	C	G	G	G	E	E	E	E	J	J	J	J	J	J	
	2.2	A	A	A	C	C	G	G	G	E	E	E	E	J	J	J	J	J	J	
	2.7	A	A	A	C	C	G	G	G	E	E	E	E	J	J	J	J	J	J	
	3.3	A	A	A	C	C	G	G	G	E	E	E	E	J	J	J	J	J	J	
	3.9	A	A	A	C	C	G	G	G	E	E	E	E	J	J	J	J	J	J	
	4.7	A	A	A	C	C	G	G	G	E	E	E	E	J	J	J	J	J	J	
	5.6	A	A	A	C	C	G	G	G	E	E	E	E	J	J	J	J	J	J	
	6.8	A	A	A	C	C	G	G	G	E	E	E	E	J	J	J	J	J	J	
	8.2	A	A	A	C	C	G	G	G	E	E	E	E	J	J	J	J	J	J	
	10	A	A	A	C	C	G	G	G	E	E	E	E	J	J	J	J	J	J	
	12	A	A	A	C	C	G	G	G	E	E	E	E	J	J	J	J	J	J	
	15	A	A	A	C	C	G	G	G	E	E	E	E	J	J	J	J	J	J	
	18	A	A	A	C	C	G	G	G	E	E	E	E	J	J	J	J	J	J	
	22	A	A	A	C	C	G	G	G	E	E	E	E	J	J	J	J	J	J	
	27	A	A	A	C	C	G	G	G	E	E	E	E	J	J	J	J	J	J	
	33	A	A	A	C	C	G	G	G	E	E	E	E	J	J	J	J	J	J	
	39	A	A	A	C	C	G	G	G	E	E	E	E	J	J	J	J	J	J	
	47	A	A	A	C	C	G	G	G	E	E	E	E	J	J	J	J	J	J	
	56	A	A		C	C	G	G	G	E	E	E	E	J	J	J	J	J	J	
	68	A	A		C	C	G	G	G	E	E	E	E	J	J	J	J	J	J	
	82	A			C	C	G	G	G	E	E	E	E	J	J	J	J	J	J	
	100	A			C	C	G	G	G	E	E	E	E	J	J	J	J	J	J	
	120				C	C	G	G	G	E	E	E	E	J	J	J	J	J	J	
	150				C	C	G	G	G	E	E	E	E	J	J	J	J	J	J	
	180				C	C	G	G	G	E	E	E	E	J	J	J	J	J	J	
	220				C	C	G	G	G	E	E	E	E	J	J	J	J	J	J	
	270				C	C	G	G	G	E	E	E	E	M	J	J	J	J	J	
	330				C	C	G	G	G	E	E	E	E	M	J	J	J	J	J	
	390						G	G	G	J	J	J	J	M	J	J	J	J	J	
	470						G	G	G	J	J	J	J	M	J	J	J	J	J	
	560						G	G	G	J	J	J	J	J	J	J	J	J	J	
	680						G	G	G	J	J	J	J	J	J	J	J	J	J	
	820						G	G	G	J	J	J	J	J	J	J	J	J	M	
	1000						G	G	G	J	J	J	J	J	J	J	J	J	Q	
	1200						G	G	G	J	J	J	J	J	J	J	J	J	Q	
	1500						G	G	G	J	J	J	J	J	J	J	J	J	M	
	1800									J	J	J	J	J	J	M	M	M		
	2200									J	J	J	J	M	J	J	M	P		
	2700									J	J	J	J	M	J	J	M	P		
	3300									N	N	N	N	N	J	J	M	P		
	3900									N	N	N	N	N	J	J	M	P		
	4700									N	N	N	N	N	J	J	M	P		
	5600									N	N	N	N	N	J	J	M	M		
	6800									N	N	N	N	N	M	M	M	M		
	8200									N	N	N	N	N	M	M	M	M		
Cap (pF)	0.010																			
	0.012																			
	0.015																			
	0.018																			
	0.022																			
	0.027																			
	0.033																			
	0.039																			
	0.047																			
	0.068																			
	0.082																			
	0.1																			
WVDC	10	16	25	16	25	50	6.3	25	50	100	16	25	50	100	200	16	25	50	100	200
SIZE	0201			0402			0603			0805					1206					
Letter	A	C	E	G	J	K	M	N	P	Q	X	Y	Z	BB	CC					
Max. Thickness	0.33 (0.013)	0.56 (0.022)	0.71 (0.028)	0.86 (0.034)	0.94 (0.037)	1.02 (0.040)	1.27 (0.050)	1.40 (0.055)	1.52 (0.060)	1.78 (0.070)	2.29 (0.090)	2.54 (0.100)	2.79 (0.110)	3.05 (0.120)	3.175 (0.125)					
	PAPER					EMBOSS					EMBOSS									

Contact Factory for Multiples

# C0G (NP0) Dielectric

## Capacitance Range



PREFERRED SIZES ARE SHADED

SIZE	1210				1812				1825				2220				2225				
Soldering	Reflow/Wave				Reflow Only				Reflow Only				Reflow Only				Reflow Only				
Packaging	Paper/Embossed				All Embossed				All Embossed				All Embossed				All Embossed				
(L) Length	MM (in.)	3.20 ± 0.20 (0.126 ± 0.008)			4.50 ± 0.30 (0.177 ± 0.012)				4.50 ± 0.30 (0.177 ± 0.012)				5.70 ± 0.40 (0.224 ± 0.016)				5.72 ± 0.25 (0.225 ± 0.010)				
(W) Width	MM (in.)	2.50 ± 0.20 (0.098 ± 0.008)			3.20 ± 0.20 (0.126 ± 0.008)				6.40 ± 0.40 (0.252 ± 0.016)				5.00 ± 0.40 (0.197 ± 0.016)				6.35 ± 0.25 (0.250 ± 0.010)				
(t) Terminal	MM (in.)	0.50 ± 0.25 (0.020 ± 0.010)			0.61 ± 0.36 (0.024 ± 0.014)				0.61 ± 0.36 (0.024 ± 0.014)				0.64 ± 0.39 (0.028 ± 0.015)				0.64 ± 0.39 (0.025 ± 0.015)				
WVDC	25	50	100	200	25	50	100	200	50	100	200	50	100	200	50	100	200	50	100	200	
Cap (pF)	0.5 1.0 1.2 1.5																				
	1.8 2.2 2.7																				
	3.3 3.9 4.7																				
	5.6 6.8 8.2																				
	10 12 15																				
	18 22 27																				
	33 39 47																				
	56 68 82																				
	100 120 150																				
	180 220 270																				
	330 390 470																				
	560 680 820	J	J	J	J																
	1000 1200 1500	J	J	J	M	K	K	K	K	M	M	M	X	X	X	P	P	P	P	P	
	1800 2200 2700	J	J	J	M	K	K	K	K	M	M	M	X	X	X	P	P	P	P	P	
	3300 3900 4700	J	J	M	M	K	K	K	P	M	M	M	X	X	X	P	P	P	P	P	
	5600 6800 8200	J	J	M	M	K	M	M	P	M	M	M	X	X	X	P	P	P	P	P	
Cap (μF)	0.010 0.012 0.015	N	N	N		K	P	P	X	M	M	M	X	X	X	P	P	P	P	P	
	0.018 0.022 0.027				M	P			M	P	P	M	X	X	X	P	P	Y	Y	Y	
	0.033 0.039 0.047				M	CC			M	CC	P		X	X		P	Y	Y	Y		
	0.068 0.082 0.1				CC	CC			CC	CC						P	P	P			
WVDC	25	50	100	200	25	50	100	200	50	100	200	50	100	200	50	100	200	50	100	200	
SIZE	1210				1812				1825				2220				2225				
Letter	A	C	E	G	J	K	M	N	P	Q	X	Y	Z	BB	CC						
Max. Thickness	0.33 (0.013)	0.56 (0.022)	0.71 (0.028)	0.86 (0.034)	0.94 (0.037)	1.02 (0.040)	1.27 (0.050)	1.40 (0.055)	1.52 (0.060)	1.78 (0.070)	2.29 (0.090)	2.54 (0.100)	2.79 (0.110)	3.05 (0.120)	3.175 (0.125)						
	PAPER					EMBORESSED															

Contact Factory for Multiples

